

## Fluon<sup>®</sup> FC 15 MIN *Typical Properties*

### DESCRIPTION

Fluon<sup>®</sup> FC 15 MIN (310 154 464) is a 15% wollastonite-filled PTFE product. This compound is supplied dry powder form.

### TYPICAL PHYSICAL PROPERTIES

Property	Test Method	Units	Typical Property
Specific Gravity	ASTM D-4745		2.23
Filler Content	ASTM D-4745	%	15
Tensile Strength	ASTM D-4745	PSI	3,500
Elongation	ASTM D-4745	%	250
Deformation Under Load	AGC Chemicals	%	10
Hardness	ASTM D-2240		
Peak		Shore D	62
Sustained		Shore D	60

### END USES

Wollastonite fibers are added to PTFE to improve the wear properties, abrasion, compressive strength, and creep resistance of PTFE without sacrificing the chemical and thermal resistance of the polymer.

### PROCESSING

This product can be processed using compression molding equipment to mold thick-walled parts.

Fluon<sup>®</sup> is a registered trademark of Asahi Glass Company, LTD.

The information provided herein is related only to the specific product designated and may not be applicable where such product is used in combination with any other materials or in any process. NO REPRESENTATION OR WARRANTIES, EITHER EXPRESSED OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE, ARE MADE HEREUNDER. The user of this product has the sole responsibility to determine the suitability of the product for any use and manner of use intended. This document may be revised after its issuance, and the user is advised to use the latest revision.

# Fluon® FC 15 MIN *Typical Properties*

## PACKAGING

Fluon® FC 15 MIN is packaged in a lined cardboard fiber drum containing 130 pounds.

## HANDLING PRECAUTIONS

Heating Fluon® products in excess of 750°F (399°C) can produce toxic fumes. It is, therefore, necessary to provide local exhaust ventilation in areas where Fluon® products are exposed to high temperatures. Avoid breathing fumes or contaminating smoking tobacco with fumes, powder, or dust.

Thermal decomposition of this product will generate hydrogen fluoride, which is corrosive. Corrosion resistance materials are required for prolonged contact with molten resin.

## SAFE HANDLING INFORMATION

A summary of the hazards, as defined by OSHA Hazard Communication Standard, 29 CFR 1910.1200 for this product are:

Physical hazards: None

Health hazards: None

FOR ADDITIONAL INFORMATION AND HANDLING INSTRUCTIONS READ AGC CHEMICALS AMERICAS, INC. MATERIAL SAFETY DATA SHEET.

### For more information and samples contact

**AGC Chemicals Americas, Inc.**

55 E. Uwchlan Avenue, Suite 201  
Exton, PA 19341

**Phone:** (800) 424-PTFE (7833)

**Fax:** (610) 423-4301

Fluon® is a registered trademark of AGC Chemicals Americas, Inc.

FC 15 MIN.docx Rev. 10/2010