

## Fluon<sup>®</sup> FP-EF-101 Typical Properties

### DESCRIPTION

Fluon<sup>®</sup> FP-EF-101 (464 102 517) is a 5% glass reinforced ETFE product designed for use in injection molding or extrusion applications. The glass fibers are added to improve the physical properties of ETFE. This compound is supplied in cylindrical pellet form. These pellets are approximately 0.125" long by 0.100" diameter.

### TYPICAL PHYSICAL PROPERTIES

Property	Test Method	Units	Typical Property
Melt Flow Rate	ASTM D-2116	g/10 minutes	5.5
Specific Gravity	ASTM D-792		1.78
Bulk Density	ASTM D-1895	grams/liter	950
Nominal Filler	AGC	%	5.0
Tensile Strength	ASTM D-638	psi	5,000
Elongation	ASTM D-638	%	50
Flexural Modulus	ASTM D-790	psi	225,000
Flexural Strength	ASTM D-790	psi	6,000
Notched Izod	ASTM D-256	ft-lb/in	12.5
HDT @ 0.45 MPa	ASTM D-648	°C	228

### END USES

Demanding applications where the thermal and chemical resistance of ETFE is required with additional mechanical toughness provided by glass-fiber reinforcement.

### PROCESSING

This product can be processed using standard ETFE condition in conventional thermoplastic techniques such as injection molding and melts extrusion.

Fluon<sup>®</sup> is a registered trademark of Asahi Glass Company, LTD.

The information provided herein is related only to the specific product designated and may not be applicable where such product is used in combination with any other materials or in any process. NO REPRESENTATION OR WARRANTIES, EITHER EXPRESSED OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE, ARE MADE HEREUNDER. The user of this product has the sole responsibility to determine the suitability of the product for any use and manner of use intended. This document may be revised after its issuance, and the user is advised to use the latest revision.

**AGC**  
AGC Chemicals Americas, Inc.  
Business & Technical Center  
55 E. Uwchlan Ave, Suite 201  
Exton, PA 19341  
Phone: 610.423.4300  
Fax: 610.423.4301  
<http://www.agcchem.com>

# Fluon<sup>®</sup> FP-EF-101 *Typical Properties*

## PACKAGING

Fluon<sup>®</sup> FP-EF-101 is packed in fiber drums containing 130 pounds.

## HANDLING PRECAUTIONS

Heating Fluon<sup>®</sup> products in excess of 750°F (399°C) can produce toxic fumes. It is, therefore, necessary to provide local exhaust ventilation in areas where Fluon<sup>®</sup> products are exposed to high temperatures. Avoid breathing fumes or contaminating smoking tobacco with fumes, powder, or dust.

Thermal decomposition of this product will generate hydrogen fluoride, which is corrosive. Corrosion resistance materials are required for prolonged contact with molten resin.

## SAFE HANDLING INFORMATION

A summary of the hazards, as defined by OSHA Hazard Communication Standard, 29 CFR 1910.1200 for this product are:

Physical hazards: None

Health hazards: None

FOR ADDITIONAL INFORMATION AND HANDLING INSTRUCTIONS READ AGC CHEMICALS AMERICAS, INC. MATERIAL SAFETY DATA SHEET.

### For more information and samples contact

**AGC Chemicals Americas, Inc.**  
55 E. Uwchlan Avenue, Suite 201  
Exton, PA 19341

**Phone:** (800) 424-PTFE (7833)

**Fax:** (610) 423-4301

Fluon<sup>®</sup> is a registered trademark of AGC Chemicals Americas, Inc.

FP-EF-101.DOC Rev. 04/2010