

## 10% Sulfuric Acid compatibility with AFLAS®



**Test method** Soaked into the fluid at 100°C for 70 hours  
**Test fluid** 10% sulfuric acid (10% H<sub>2</sub>SO<sub>4</sub> aq)  
**Test piece** AFLAS® 100S

<b>Formulation</b>	AFLAS® 100S	100
	MT-Carbon(N990)	20
	TAIC*	5
	Perkadox® 14**	1
	Sodium Stearate	1

(phr)

**Cure Conditions** Press molded at 170C for 20min  
 Post cured at 200C for 4h

Properties (before test)	AFLAS® 100S	FKM (polyol cure)	3-FKM (peroxide cure)
Tensile strength [MPa]	24	17	24
Tensile Elongation [%]	270	270	370
Hardness [shore-A]	65	73	67

10% Sulfuric acid compatibility 100 °C for 70 hours	AFLAS® 100S	FKM (polyol cure)	3-FKM (peroxide cure)
Change of Tensile Strength [%]	-3	-12	-4
Change of Tensile Elongation [%]	5	2	-1
Change in Hardness [points]	5	-1	1
Volume change [%]	0.9	1.3	0

\* Triallylisocyanurate

\*\* 1,3-bis(t-butylperoxy)-diisopropylbenzene. Perkadox® is a registered trademark of Akzo Nobel Chemicals B.V.