

Fluon[®] Conductive AH-ETFE Typical Properties

DESCRIPTION

Fluon[®] conductive AH-ETFE are a series of compounds designed for use in automotive fuel hose. This group of products is ideal for hose constructions which require chemical resistance, permeation resistance, and unsurpassed protection against static build-up. These products are supplied in cylindrical pellet form. These pellets are approximately 0.080" diameter x 0.125" long.

TYPICAL PHYSICAL PROPERTIES

Property	Test Method	Units	Fluon LM-ETFE AH-600C	Fluon ETFE AH-700C	Fluon ETFE AH-800C
Melt Flow Rate	ASTM D-3159	g/10 min	4	2	5.5
Bulk Density	ASTM D-1895	g/L	975	975	975
Melt Point	AGC Internal	deg C	230	258	255
Specific Gravity	ASTM D-3159	-	1.76	1.75	1.75
Surface Resistivity	AGC Internal	Ω/square	1x10 ³	1x10 ³	1x10 ³

NOTE: The data listed here represents typical values for the stated grades of Fluon[®] Melt Processable Compounds. This information should be used as a guide only and not to establish specification limits or design criteria. AGC Chemicals Americas assumes no obligation or liability for any advice furnished by us or for results obtained with respect to this product. All such advice is provided free of charge and the buyer assumes sole responsibility for results obtained in reliance thereon.

BENEFITS

AH-600C offers a lower melting compound that results in a wider process window and better compatibility with some polyamide nylons for co-extrusion; AH-700C balances performance and economics; AH-800C has a higher upper-end temperature rating (approaching 200°C) and improved resistance to stress cracks at elevated temperatures. Can be customized to specifications.

APPLICATIONS

- Automotive fuel hose
- AC compressor hose
- Film & battery applications
- Multi-layer film

PROCESSING

Fluon AH-ETFE fluoropolymer resins can be processed using conventional melt processable techniques including extrusion, injection molding, blow molding, compression molding, and transfer molding. It is strongly recommended that process equipment exposed to molten resin be made of corrosion-resistant metals such as Monel, Inconel, or Hastelloy.

Fluon[®] is a registered trademark of Asahi Glass Company, LTD.

The information provided herein is related only to the specific product designated and may not be applicable where such product is used in combination with any other materials or in any process. NO REPRESENTATION OR WARRANTIES, EITHER EXPRESSED OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE, ARE MADE HEREUNDER. The user of this product has the sole responsibility to determine the suitability of the product for any use and manner of use intended. This document may be revised after its issuance, and the user is advised to use the latest revision.

Fluon® Conductive AH-ETFE *Typical Properties*

HANDLING PRECAUTIONS

Heating Fluon® products in excess of 750°F (399°C) can produce toxic fumes. It is, therefore, necessary to provide local exhaust ventilation in areas where Fluon® products are exposed to high temperatures. Avoid breathing fumes or contaminating smoking tobacco with fumes, powder, or dust.

Thermal decomposition of this product will generate hydrogen fluoride, which is corrosive. Corrosion resistance materials are required for prolonged contact with molten resin.

STORAGE

The properties of Fluon AH-ETFE are not impacted by storage time. Storage and handling facilities should be designed to minimize contact with airborne contamination and the formation of condensation on the resin. Fluoropolymers are not hygroscopic and will not typically need to be dried prior to use. However, masterbatches and conductives may contain materials that do absorb water and should be dried prior to use.

SAFE HANDLING INFORMATION

A summary of the hazards, as defined by OSHA Hazard Communication Standard, 29 CFR 1910.1200 for this product are:

Physical hazards: None

Health hazards: None

FOR ADDITIONAL INFORMATION AND HANDLING INSTRUCTIONS READ AGC CHEMICALS AMERICAS, INC. MATERIAL SAFETY DATA SHEET.

For more information and samples contact

AGC FluoroCompounds Group

A Division of AGC Chemicals Americas, Inc.
55 E. Uwchlan Avenue, Suite 201
Exton, PA 19341

Phone: (800) 424-7833 USA Only
(610) 423-4300

Fax: (610) 423-4301

Fluon® is a registered trademark of AGC Chemicals Americas, Inc.

Fluon Conductive AH-ETFE.DOC 07/2015