

## FL1710 Typical Properties

### PRODUCT DESCRIPTION

FL1710 is a white finely divided PTFE (polytetrafluoroethylene) micropowder which is easy to disperse in a wide range of liquids. FL1710 is particularly suitable for use in surface coatings, metal decorating inks, low viscosity lubricating oils and is readily dispersed in liquids using either high or low shear mixing. This combination of properties makes FL 1710 very useful in coating formulations. FL1710 is suitable for use in food contact applications.

### TYPICAL PROPERTIES

Property	Test Method	Units	Typical Value
Bulk Density	ASTM D-4894	grams/liter	400
Particle Size – Low Shear	Laser Diffraction	Average (µm)	5
		D10	5
		D90	25
Particle Size	Hegman ASTM D-1210	microns	3
Surface Area	Krypton adsorption	meter <sup>2</sup> /gram	2.3
Moisture Content	ASTM D-4019	%	< 0.1
Particle Type	AGC Chemicals Americas	Soft, round sub-micron particles in clusters	
FDA Compliance	CFR Number	CFR 175.300, CFR 177.1550	
Melting Point	ASTM D-3417	°F (°C)	633 (334)
Volatile Content	AGC Chemicals Americas	%	0.06
Particle Smear Sensitivity	AGC Chemicals Americas	Cluster break-up to smaller size upon mixing	
Oil Absorption	ASTM D-1438	lb oil / 100 lb	45
Oil Penetrometer	ASTM D-1403	1 / 10 mm	99

Fluon<sup>®</sup> is a registered trademark of Asahi Glass Company, LTD.

The information provided herein is related only to the specific product designated and may not be applicable where such product is used in combination with any other materials or in any process. NO REPRESENTATION OR WARRANTIES, EITHER EXPRESSED OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE, ARE MADE HEREUNDER. The user of this product has the sole responsibility to determine the suitability of the product for any use and manner of use intended. This document may be revised after its issuance, and the user is advised to use the latest revision.

## FL1710 *Typical Properties*

### HANDLING PRECAUTIONS

Heating Fluon® products in excess of 750°F (399°C) can produce toxic fumes. It is, therefore, necessary to provide local exhaust ventilation in areas where Fluon® products are exposed to high temperatures. Avoid breathing fumes or contaminating smoking tobacco with fumes, powder, or dust.

Thermal decomposition of this product will generate hydrogen fluoride, which is corrosive. Corrosion resistance materials are required for prolonged contact with molten resin.

### SAFE HANDLING INFORMATION

A summary of the hazards, as defined by OSHA Hazard Communication Standard, 29 CFR 1910.1200 for this product are:

Physical hazards: None

Health hazards: None

FOR ADDITIONAL INFORMATION AND HANDLING INSTRUCTIONS READ AGC CHEMICALS AMERICAS, INC. MATERIAL SAFETY DATA SHEET.

#### For more information and samples contact

**AGC Chemicals Americas, Inc.**  
55 E. Uwchlan Avenue, Suite 201  
Exton, PA 19341

**Phone:** (800) 424-PTFE (7833)

**Fax:** (610) 423-4301